

DIVISION: 06 00 00 – WOOD, PLASTICS, AND COMPOSITES
Section: 06 05 73.13 – Fire-Retardant Wood Treatment

REPORT HOLDER:
Fire Retardant Coatings of Texas, LLC
4500 Grants Lane
Fort Worth, TX 76119
USA
(817) 710-5233
www.frctexas.com

REPORT SUBJECT:
FX Lumber Guard and FX Lumber Guard XT Fire Retardant Penetrant

1.0 SCOPE OF EVALUATION

1.1 This Research Report addresses compliance with the following Codes:

- 2021, 2018, 2015 *International Building Code*® (IBC)
- 2021, 2018, 2015 *International Residential Code*® (IRC)
- 2021, 2018, 2015 *International Fire Code*® (IFC)
- 2021, 2018, 2015 *International Existing Building Code*® (IEBC)

NOTE: This report references the most recent edition of the codes cited. Section numbers in earlier editions of the codes may differ.

1.2 FX Lumber Guard and FX Lumber Guard XT have been evaluated for the following properties (see Table 1):

- Surface burning characteristics

1.3 FX Lumber Guard and FX Lumber Guard XT are recognized in this report for the following uses:

- To reduce the flame-spread classification of the lumber or plywood to achieve the flame-spread and smoke-developed indices required by the applicable Code
- Surface application to unfinished surfaces of Southern Yellow Pine, Spruce-Pine-Fir, Hem Fir, and Douglas Fir dimensional lumber, and Southern Yellow Pine and Douglas Fir plywood, and OSB sheathing.

2.0 STATEMENT OF COMPLIANCE

FX Lumber Guard and FX Lumber Guard XT comply with the Codes listed in Section 1.1, for the properties stated in Section 1.2, and uses stated in Section 1.3, when installed as described in this report, including the Conditions of Use stated in Section 6.0.

3.0 DESCRIPTION

FX Lumber Guard and FX Lumber Guard XT are fire retardant penetrants applied and used in accordance with IFC Section 803.4. They are clear, water-based products supplied in 1-quart, 1-gallon, and 5-gallon containers, 55-gallon drums, and 250-gallon totes. The products have a shelf life of three years when stored in sealed containers at temperatures between 45°F and 95°F.

4.0 PERFORMANCE CHARACTERISTICS

4.1 Surface Burning Characteristics: When applied to unfinished dimensional Southern Yellow Pine, SPF, Hem Fir, and Douglas Fir lumber or Southern Yellow Pine and Douglas Fir plywood, or OSB sheathing, at a coverage rate of 300 to 350 square feet per gallon, the treated wood provides a flame-spread index of 25 or less and a smoke-developed index of 200 or less when tested in accordance with ASTM E84 or UL723, and qualifies as a Class A finish in accordance with IBC Section 803.1, IFC Section 803.1.2, and NFPA 703.

5.0 INSTALLATION

5.1 General: FX Lumber Guard and FX Lumber Guard XT must be applied in accordance with the manufacturer's published installation instructions, the applicable Code, and this Research Report. The products have not been evaluated for use on surfaces that are subjected to washing or a sustained humidity of 80% or more. The products have not been evaluated for overcoating.



5.2 Field Application: The manufacturer's published installation instructions and this Research Report must be strictly adhered to, and a copy of the instructions must be available on the jobsite at all times during installation.

The products are field-applied by spraying, rolling, or brushing in a one-coat application. The products must be agitated before and throughout the application. The air temperature during application must not be below 45°F or above 95°F. The maximum moisture content for the substrate must not exceed 15% for dimensional lumber or 19% for plywood or OSB. The cure time is between 8 to 32 hours depending on air temperature. The material being treated must be clean, dry, and free from dirt, grease, oil, and all coatings such as paint, stains, and sealers. The products must be applied by field applicators approved by FRCT, showing sufficient evidence that they possess the knowledge and equipment to conform with the application procedures of Fire Retardant Coatings of Texas.

5.2.1 Field Test: When observation of the treatment and/or field testing is required by the Code Official, such field testing must be conducted as follows:

The treated substrate will not have distinctive observable features. To ensure the substrate has been treated properly, the treated substrate must be exposed to the flame from a small fire source, such as a propane torch, applied to both a treated sample and an untreated sample for a period of not less than 15 seconds. The presence of the treatment is observable by comparison of the reactions of the substrates to the flame. Treated substrates will form a black char layer.

5.3 Factory-applied Coatings: The FX Lumber Guard and FX Lumber Guard XT may be applied to substrates noted in Section 1.3 by the approved applicators at the locations noted in Table 2.

6.0 CONDITIONS OF USE

6.1 Installation must comply with this Research Report, the manufacturer's published installation instructions, and the applicable Code. In the event of a conflict between the manufacturer's instructions and this report, this report governs.

6.2 Application is limited to the specific substrates set forth in Section 1.3.

6.3 Use of the product is limited to exposed interior locations having a sustained humidity of less than 80 percent.

6.4 Field testing must be performed by the approved applicator, as indicated in Section 5.3, when required by the Code Official.

6.5 For field-applied penetrants, a Certificate of Fire Retardant Treatment, as shown in Figure 1, must be submitted by the field applicator to the Code Official describing the material treated; the location of the treated materials, product batch number or order number, including the square footage of the area treated; and the application rate.

6.6 Factory-applied penetrants must be done by one of the approved applicators in Table 2 and must be labeled as described in Section 8 and as shown in Figure 2.

6.7 Special inspections may be required when determined to be necessary by the Code Official in accordance with IBC Section 1705.1.1, as applicable.

6.8 The products are manufactured in Haslet, Texas, under a quality control program with inspections by Intertek Testing Services NA, Inc.

7.0 SUPPORTING EVIDENCE

7.1 Data in accordance with the ICC-ES Acceptance Criteria for Surface-applied Fire Retardant Coatings (AC363), dated February 2007 (editorially revised March 2012), and with NFPA 703, Standard for Fire Retardant Treated Wood and Fire Retardant Coatings for Building Materials, 2018 edition.

7.2 Intertek Listing Report "[FX Lumber Guard and FX Lumber Guard XT](#)".

8.0 IDENTIFICATION

8.1 Containers: The FX Lumber Guard and FX Lumber Guard XT containers are identified by a marking bearing the report holder's name (Fire Retardant Coatings of Texas)





and address, the product name, batch number (BC#), date of manufacture, shelf life, application instructions, the Intertek Mark as shown below, and the Code Compliance Research Report number (CCRR-1044).



8.2 Factory-applied Penetrants: Lumber, plywood, and OSB treated at one of the approved applicators noted in Table 2 must be identified by a label bearing the applicator’s name, the report holder’s name (Fire Retardant Coatings of Texas), the product name, and the Intertek Mark. See Figure 2.

9.0 OTHER CODES

This section is not applicable.

10.0 CODE COMPLIANCE RESEARCH REPORT USE

10.1 Approval of building products and/or materials can only be granted by a building official having legal authority in the specific jurisdiction where approval is sought.

10.2 Code Compliance Research Reports shall not be used in any manner that implies an endorsement of the product by Intertek.

10.3 Reference to the <https://bpdirectory.intertek.com> is recommended to ascertain the current version and status of this report.

This Code Compliance Research Report (“Report”) is for the exclusive use of Intertek’s Client and is provided pursuant to the agreement between Intertek and its Client. Intertek’s responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this Report. Only the Client is authorized to permit copying or distribution of this Report and then only in its entirety, and the Client shall not use the Report in a misleading manner. Client further agrees and understands that reliance upon the Report is limited to the representations made therein. The Report is not an endorsement or recommendation for use of the subject and/or product described herein. This Report is not the Intertek Listing Report covering the subject product and utilized for Intertek Certification and this Report does not represent authorization for the use of any Intertek certification marks. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek.





TABLE 1 - PROPERTIES EVALUATED

PROPERTY	IBC SECTION	IRC SECTION	IFC SECTION	IEBC SECTION
Surface burning characteristics	803.1	R302.9	803.1.1, 803.4	1204.9

TABLE 2 – APPROVED FACTORY-APPLICATOR LOCATIONS

MANUFACTURER	LOCATION	INTERTEK CONTROL NUMBER
AccuTreated	Deer Park, NY	5010437
Global Fireproof Solutions, Inc.	Groveland, FL	5011703
	Cartersville, GA	5010908
Precision Applied Coatings Enterprises (PACE)	Frazeyburg, OH	5011817
Chicago Flameproof and Wood Specialties Corp.	Montgomery, IL	5011723
Chicago Flameproof and Wood Specialties Corp. –DBA North Texas Flameproof and Wood Specialties	Fort Worth, TX	5011701
Chicago Flameproof and Wood Specialties Corp. – DBA East Coast Flameproof	Kinsale, VA	5027245





Fire Retardant Coatings of Texas®, LLC
 1150 Blue Mound Rd West #403 • Haslet, Texas 76052
 Office (817) 710-5233 Fax (817) 439-8385
 www.frctexas.com

FX LumberGuard
Certificate of Fire Retardant Treatment

To: _____ Date of Service: _____

Batch Code or Order No.: _____
 This is to certify that the material described below was treated with FX Lumber Guard and has been applied in conformance with FRCT's application specifications and Intertek Research Report CCRR-xxxx.
 Your Invoice # _____ dated _____ 20____.

Description of material treated: _____

Square Foot Treated: _____ Spread Rate: _____

Applicator:
 Name: _____
 Address: _____
 City: _____ ST: _____ ZIP: _____
 Phone: _____

Applicators Signature: _____

Fire Retardant Coatings of Texas is a federally registered trademark

Figure 1 – Example of Certificate of Treatment (field application)






Company Name	
Applicator of Fire Retardant Coatings of Texas - FX Lumber Guard/FX Lumber Guard XT	
 Intertek Control # XXXXXXXX	CERTIFIED TO: ASTM E84 Flame Spread < 25 Smoke Development < 200 Class A
Refer to Intertek's Directory of Building Products (http://bpdirectory.intertek.com) for detailed information	

Figure 2 – Example of Factory Applicator Label

